




CERTIFIED MATERIAL REPORT



www.QuehanHyundai.com

Trade Name	SMT-308L	Size	1.2 mm x 15Kg							
Lot No.	N030812	Purchaser's Order No.	HWC-250429V1							
Specification	AWS A5.9 ER308L		* According to EN 10204-2004 : 3.1							
Welding Current	-	Shielding Gas	-	Post Weld Heat Treatment (°C×hr.)	-					
Mechanical Properties										
Weld Metal	Tensile Test			Impact Test (CVN - Joule)						
	YS (MPa)	TS (MPa)	EL (%)	Temp. (°C)	X ₁	X ₂	X ₃	Avg.		
	445	585	39.0	-	-	-	-	-		
AWS Spec.	-	-	-	-						
Chemical Composition (%)										
Weld Metal	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	
	0.019	0.56	2.24	0.020	0.009	0.04	9.52	19.69	0.02	
AWS Spec.	≤0.03	0.30 ~0.65	1.0 ~2.5	≤0.03	≤0.03	≤0.75	9.0 ~11.0	19.5 ~22.0	≤0.75	
Others										
* Q'ty: 600 kg										
We hereby certify that the material covered by this report has been inspected in accordance with and been found to meet the applicable requirements of specification and customer's requirements.										
<p>Approved by</p>  <p>QA Manager Pham Dinh Anh Vu</p>										

HYUNDAI WELDING VINA CO., LTD.